

STARTER

Underlayment for
Laminate Floors

plus



Technical Data Sheet:

Properties	Test Method	Performance
Gauge	mm	1.5
Density	lbs	2
Compressive Strength Vertical Direction (psi)	ASTM D3575-93 Suffix D @ 25% / 50%	3.0 11.5
Tensile Strength (psi) (@ Each Thickness)	ASTM D3575-93 Suffix T MD / CMD	68.0 25.0
Elongation (%)	ASTM D3575-93 Suffix T MD / CMD	19.0 8.5
Tear Resistance (lb/ft3) (@ Each Thickness)	ASTM D3575-93 Suffix T MD / CMD	9.0 14.5
Density Range (lb/ft3)	ASTM D3575-93	1.85 to 2.2
Water Vapor Transmission Rate GM / 100 in2 / 24 hr.	ASTM F-1249 Method 3005 FED STD 101	0.090 0.090

IMPORTANT NOTICE:

The above specifications were collected in a controlled environment. This information relates only to StarterPlus ECO and does not take into consideration the floor system and environment into which it will be used. Individual floor systems may affect the performance of StarterPlus ECO. Proper sub-floor preparations and following the finished floor manufacturer's instructions is crucial to a successful installation. Further information about these tests is available.