



For Laminates, Hardwood
and Engineered

Technical Data Sheet

Properties	Method	Performance
Zero VOC	ASTM D 5116 & California's Section 01350	B.Q.L Below Quantifiable Levels
Acoustical	ASTM E 2179-03	Delta 21
	ASTM E 492-4 & E 989-89	IIC 73
	ASTM E 90-04 & E 413-04	STC 72
Thickness	ASTM-D3575	2.0 mm
Water Vapor Transmission Rate	ASTM E 96	0.31 lbs/24 hrs/1000 sq. ft
Impact Resistance	ISO/DIS 24335 NALFA LF01-2003 Large Ball Test	1100 mm Commercial
Compression Resistance	ASTM D3575 Suffix D	8 lbs/in ²
Compression Set	ASTM D3575 Suffix B	30.00%
Compression Creep	EN 1606 / EN 13163	10% (12 kPa)
Tensile Strength	ASTM-D-3575	95 lbs/in ²
Thermal Resistance	ASTM-C-518	3.8 Max temperature 95°C (203°F)

IMPORTANT NOTICE:

The above specifications were collected in a controlled environment. This information relates only to Natural and does not take into consideration the floor system and environment into which it will be used. Individual floor systems may affect the performance of Natural. Proper sub-floor preparations and following the finished floor manufacturer's instructions is crucial to a successful installation. Further information about these tests is available.